

Dulux Exterior Waterproof Sealer A930-58160

| Typical Uses | As a waterproof base coat to be applied on exterior wall surfaces or roofs. | | | | | | | | |
|--|--|-----------------|----------|-----------------|---|--------------------|--|-------------------------------|--|
| Advantages | <ul style="list-style-type: none"> • Durable, waterproof, anti-cracking with strong tenacity • High adherence on PU, corrugated sheets and tiles • Good permeability seals holes and gaps • 12x resilience | | | | | | | | |
| Pack Size | 1 Gal, 5 Gal | | | | | | | | |
| Colour Range | Transparent | | | | | | | | |
| Finish | Gloss | | | | | | | | |
| Composition | Water-based Synthetic Resin, Additives, Water | | | | | | | | |
| Thinning | Water | | | | | | | | |
| Weight Solids | Over 25% | | | | | | | | |
| Theoretical Coverage | Theoretically, 1 gallon of this product can cover 50 sqm in one coat. Coverage will vary considerably depending on application methods, surface roughness, surface porosity and other factors. | | | | | | | | |
| Coat Resistances | | | | | | | | | |
| - Extensibility | Over 1200%, passed extensibility test under ASTM D412-06ae2 standard. | | | | | | | | |
| - Alkali-resistance | The coat does not show any wrinkle, crack, swelling or spalling in the 48-hour immersion in alkaline liquid, passed CNS 10757 alkali-resistance test standard. | | | | | | | | |
| - Water-resistance | The coat does not show any wrinkle, crack, swelling or spalling in the 72-hour immersion in water, passed CNS 10757 water-resistance test standard. | | | | | | | | |
| - Acid-resistance | The coat does not show any wrinkle, crack, swelling or spalling in the 72-hour immersion in an acidic liquid, passed CNS 10757 acid-resistance test standard. | | | | | | | | |
| Application Substrates | Old or new cement surfaces, PU, tiles, wet screenings and corrugated sheets | | | | | | | | |
| Surface Preparation | | | | | | | | | |
| - Newly Constructed Cement Surfaces | Wet substrates which have not been coated or which have been washed with water should be coated upon thorough drying. | | | | | | | | |
| - Old cement surfaces, PU, tiles, wet screenings or corrugated sheets | Old coats, seriously pulverised PU waterproof layer and rusted, loosened corrugated sheets should be scraped off, or tiles should be repaired first. The substrate should then be thoroughly cleaned using a brush or a strong jet of water. Oils, dust or loosened foreign bodies should be removed and the coat can be applied upon thorough drying of the substrate. | | | | | | | | |
| Painting System | | | | | | | | | |
| - Exterior Waterproofing | <table border="1"> <thead> <tr> <th>Number of Coats</th> <th>Thinning</th> </tr> </thead> <tbody> <tr> <td>Primer (1 coat)</td> <td>Dulux Exterior Waterproof Sealer A930-58160: 1:1 dilution with water is recommended when applying on cement surfaces. For powdery surfaces, applying in two coats is recommended to enhance its permeability and adherent power. No thinning is required when applying on non-water-absorbent surfaces such as tiles.</td> </tr> <tr> <td>Top coat (2 coats)</td> <td>Dulux Waterproof Roof A959: No thinning is required.</td> </tr> <tr> <td>Last protective coat (1 coat)</td> <td>Dulux Waterproof Coat A640: No thinning is required.</td> </tr> </tbody> </table> | Number of Coats | Thinning | Primer (1 coat) | Dulux Exterior Waterproof Sealer A930-58160 : 1:1 dilution with water is recommended when applying on cement surfaces. For powdery surfaces, applying in two coats is recommended to enhance its permeability and adherent power. No thinning is required when applying on non-water-absorbent surfaces such as tiles. | Top coat (2 coats) | Dulux Waterproof Roof A959 : No thinning is required. | Last protective coat (1 coat) | Dulux Waterproof Coat A640 : No thinning is required. |
| Number of Coats | Thinning | | | | | | | | |
| Primer (1 coat) | Dulux Exterior Waterproof Sealer A930-58160 : 1:1 dilution with water is recommended when applying on cement surfaces. For powdery surfaces, applying in two coats is recommended to enhance its permeability and adherent power. No thinning is required when applying on non-water-absorbent surfaces such as tiles. | | | | | | | | |
| Top coat (2 coats) | Dulux Waterproof Roof A959 : No thinning is required. | | | | | | | | |
| Last protective coat (1 coat) | Dulux Waterproof Coat A640 : No thinning is required. | | | | | | | | |
| - Exterior Balcony Doors & Windows Waterproofing | <table border="1"> <thead> <tr> <th>Number of Coats</th> <th>Thinning</th> </tr> </thead> <tbody> <tr> <td>Primer (1 coat)</td> <td>Dulux Exterior Waterproof Sealer A930-58160: 1:1 dilution with water is recommended when applying on cement surfaces. For powdery surfaces, applying in two coats is recommended to enhance its permeability and adherent power. No thinning is required when applying on non-water-absorbent surfaces such as tiles.</td> </tr> <tr> <td>Top coat (2 coats)</td> <td>Dulux Waterproof Coat A640: No thinning is required.</td> </tr> </tbody> </table> | Number of Coats | Thinning | Primer (1 coat) | Dulux Exterior Waterproof Sealer A930-58160 : 1:1 dilution with water is recommended when applying on cement surfaces. For powdery surfaces, applying in two coats is recommended to enhance its permeability and adherent power. No thinning is required when applying on non-water-absorbent surfaces such as tiles. | Top coat (2 coats) | Dulux Waterproof Coat A640 : No thinning is required. | | |
| Number of Coats | Thinning | | | | | | | | |
| Primer (1 coat) | Dulux Exterior Waterproof Sealer A930-58160 : 1:1 dilution with water is recommended when applying on cement surfaces. For powdery surfaces, applying in two coats is recommended to enhance its permeability and adherent power. No thinning is required when applying on non-water-absorbent surfaces such as tiles. | | | | | | | | |
| Top coat (2 coats) | Dulux Waterproof Coat A640 : No thinning is required. | | | | | | | | |

(Thinning of this product would affect its coating thickness and coverage power, which may in turn increase the number of applications needed and alter the time required for drying).

Dulux Exterior Waterproof Sealer A930-58160

Application

- 1 coat of application applied by brush, roller or spray, no thinning is required. For seriously pulverised floor surfaces, 1:1 dilution with water is recommended to enhance its permeability and adherent power.
- Carry out the works in sunny weather and at low humidity to ensure good quality.

Cleaning Up

Immediate washing of all works equipment with water upon completion of works.

Drying Time

- **Touch Dry**

At a room temperature of 29°C:

Approximately 1-2 hours

- **Recoat**

Approximately 1-2 hours

- **Thorough Drying**

The surface will become available for use after 7 days when the coating has completely dried

Safety, Health and Environmental Information

- Keep container tightly close and out of reach of children.
- A suitable cartridge mask should be worn when rubbing down.
- Ensure good ventilation during application and drying.
- Do not breathe vapour/spray.
- In case of insufficient ventilation during spraying wear suitable respiratory equipment.
- All respiratory equipment must meet (NOISH/MSHA) approved standard.
- When applying paint it is advisable to wear suitable eye protection.
- In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
- Remove splashes from skin: use soap and water or a recognised skin cleaner.
- If swallowed seek medical advice immediately and show this container or label.
- Care must be taken when transporting paint. Keep container in a secure upright position.
- Protect from extremes of temperature. Store in a cool place.
- In the event of an accident, contain and collect spillage using sand or earth. Do not empty into drains or water courses. Dispose of any paint waste in accordance with local environmental regulations.

(PLEASE REQUEST PRODUCT SAFETY DATA SHEET FROM PRODUCT DEALER AND REFER TO IT BEFORE USE.)

Type of Regulated Paint under the Air Pollution Control (Volatile Organic Compounds) Regulation of Hong Kong:
[Primers, sealers and undercoaters] VOC content (ready to use) = 11 gm/litre

LIMITATION OF LIABILITY The information detailed in this datasheet is liable to modifications from time to time in the light of experience & normal product development. To the best of our knowledge, the technical data contained herein are true and accurate at the date of issuance but are subject to change without prior notice. We guarantee our product to conform to the specifications contained herein. WE MAKE NO OTHER WARRANTY OR GUARANTEE OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND FITNESS FOR PARTICULAR PURPOSE. Liability, if any, is limited to replacement of the product or refund of the purchase price. LABOUR OR COST OF LABOUR AND OTHER CONSEQUENTIAL DAMAGES ARE HEREBY EXCLUDED.

For further information or if you have any concerns about using this product, please contact our Sales Department.

Manufactured by:

Akzo Nobel Taiwan Paints Ltd.

52 Tong Yuan Road, Chung-Li,
Taoyuan County 32063,
Taiwan

Distributed by:

Akzo Nobel Swire Paints Limited

Tel: 2823 1388 Fax: 2866 3232

Website: www.akzonobel.com

Any advice, recommendations, information, assistance or service provided by AkzoNobel in relation to goods manufactured or marketed by it or their use or any application is given in good faith. However, any advice, recommendations, information, assistance or service provided by AkzoNobel is provided without expressed or implied warranties.