



## Dulux Gloss Finish

### A365

<b>USAGE</b>	Suitable for the protection and decoration of most interior and exterior surfaces where a high-quality, durable gloss finish is required.
<b>FEATURES</b>	Long oil-modified alkyd gloss finish, containing a blend of polyurethane and silicone, and pigmented with light-fast, non-lead pigments.
<b>PACK SIZE</b>	200ml, 500ml, 1, 4 & 5 litres
<b>COLOUR RANGE</b>	Standard colours are available in the colour card for 500ml, 1, 4 & 10 litres 6,134 colours are available in Master Palette for 1 & 5 litres.
<b>TYPE OF FINISHING</b>	High gloss
<b>FILM PROPERTIES</b>	<p><b>Heat resistance :</b> General resistant to heat up to 93°C (200°F) but some discoloration of light colours may occur at temperatures above 82°C (180°F).</p> <p><b>Chemical resistance :</b> Resistant to mild chemical fume attack but where there is heavy attack, e.g. actual contact with chemicals, specialist paint systems may be required.</p> <p><b>Water resistance :</b> Resistant to levels of atmospheric humidity present in normal interior and exterior environments and will withstand repeated and frequent washing. Not suitable for use on immersed surfaces or where there is very heavy and prolonged condensation.</p>
<b>COMPOSITION</b>	<p>Pigment : Titanium Dioxide, Organic &amp; Inorganic Pigment (nonleaded)          Binder : Long oil Alkyd          Solvent : Low aromatic White Spirit</p>
<b>GLOSS LEVEL</b>	High gloss.
<b>VOLUME SOLIDS</b>	33.4 %
<b>VOC CONTENT</b>	38
<b>POT LIFE</b>	-
<b>SHELF LIFE</b>	12 months
<b>CURING TIMES</b>	<i>Single coat at standard thickness:</i>
<b>TOUCH DRY</b>	4 - 6
<b>RECOAT DRY</b>	16 - 24 hours
<b>FULL CURE</b>	24 hours
<b>FILM THICKNESS DRY</b>	25 microns
<b>FILM THICKNESS WET</b>	45 microns
<b>THEORETICAL COVERAGE</b>	16 - 17 sq.m/Litre
<b>APPLICATION METHOD</b>	Brush, roller, conventional or airless spray.
<b>SERVICE TEMPERATURE</b>	0°C - 50°C
<b>MIXING RATIO</b>	-
<b>INDUCTION</b>	-
<b>THINNING</b>	With <b>Dulux</b> Thinner 850-8 & Turpentine if required. For brush and roller application : thinning is not usually necessary.
<b>SPRAY RECOMMENDATION</b>	For conventional spray application : 10% with <b>Dulux</b> Thinner 850-8. For airless spray application : 20% with <b>Dulux</b> Thinner 850-8.



## Dulux Gloss Finish

### A365

<b>CLEANING UP</b>	Clean equipment and remove splashes from surfaces with <b>Dulux</b> Thinner 850-8 or Turpentine 850-9.
<b>SURFACE PREPARATION</b>	Surface must be clean, dry, free from all defective or poorly adhering material, dirt grease, wax etc. all surfaces should be thoroughly rubbed down using a suitable abrasive paper & then dusted off.
<b>DIRECTIONS FOR USE</b>	<p>After suitable preparation and, where necessary, priming, typical systems are as follows:</p> <p><i>Three-coat system</i></p> <p>1 coat <b>Dulux</b> Wood Aluminium Primer Sealer            2 coats <b>Dulux</b> Gloss Finish            This system is recommended for maximum durability on new work or in severe conditions.</p> <p><i>Two-coat system</i></p> <p>1 coat <b>Dulux</b> Undercoat            1 coat <b>Dulux</b> Gloss Finish            In repaint work on surfaces in good condition, or with pastel colours, the undercoat may be omitted and two coats of gloss finish applied.</p> <p>Omission of the undercoat is also recommended on heated surfaces.</p> <p><b>Note:</b> On exterior woodwork, if the wood is resinous or there is a history of blistering, it may be advantageous to use light-coloured finishes to reduce heat-absorption.</p>
<b>FLASH POINT</b>	Above 34°C (93°F).
<b>FREIGHT CLASSIFICATION</b>	Paints (Solvent Based)
<b>MSDS REFERENCE NO.</b>	Pages 6 to 9/B1.



## Dulux Gloss Finish

### A365

#### SAFETY, HEALTH AND ENVIRONMENTAL INFORMATION

#### FLAMMABLE

*Ventilation :*

Ensure good ventilation during application and drying.

*Storage :*

Keep away from heat and sources of ignition. No smoking. Keep out of reach of children.

*Fire precautions :*

For extinguishing, use foam or dry agents.

If containers are exposed to fire, keep them cool by spraying with water.

*Spills and leaks :*

Contain spillage with sand or earth. Do not allow paint to enter a drain or watercourse. Remove sources of ignition. Ventilate area.

As for normal paint waste.

#### First-aid procedures

*Inhalation :*

Move to fresh air, rest, give nothing by mouth.

*Splashes :*

*Eyes;* flush with water for at least 10 minutes, holding lids apart.

*Skin;* remove contaminated clothing, wash skin with soap and water.

If symptoms persist, seek medical guidance.

For further information or if you have any concerns about using this product contact the Sales Department at the address below:

**CIC Paints (Pvt.) Ltd**  
199, Kew Road, Colombo 2, Sri Lanka  
PO Box 352, Colombo  
Tel: +94 (01) 305777  
Fax: +94 (01) 331788  
E-mail: [cicpaint@sri.lanka.net](mailto:cicpaint@sri.lanka.net)  
Customer service hotline: +94 (074) 717474,  
+94 (01) 811563



HIGHLY  
FLAMMABLE

Any advice, recommendations, information, assistance or service provided by CIC Paints (Pvt.) Ltd in relation to goods manufactured or marketed by it or their use or any application is given in good faith. However, any advice, recommendations, information, assistance or service provided by CIC Paints (Pvt.) Ltd is provided without expressed or implied warranties.

28 Aug 2001