

Taubmans Clear Proof Exterior Clear

| | |
|------------------------------|--|
| PRODUCT NAME | Clear Proof Exterior Clear |
| PRODUCT CODE | TCLVAR |
| DESCRIPTION | Taubmans Clearproof Exterior Clear is a durable pigmented varnish based on a special resin for protection and decoration purposes. |
| USAGE | Suitable for use on all types of new or previously painted wood surfaces |
| BENEFITS | Excellent abrasion resistance Highlights the natural beauty of the grain of the wood. Water resistant, flexible and will provide long lasting protection. Its unique formulation will filter out UV rays thereby minimizing the traditional problems of cracking, flaking and peeling. |
| PACK SIZE | 1 and 5 Litres |
| COLOUR RANGE | Clear |
| FILM PROPERTIES | |
| Chemical Resistance | Resist alcohols and aliphatic hydrocarbons. Film is liable to attack from other strong solvents |
| Heat Resistance | Resistant up to 90°C |
| Water Resistance | Resistant to the atmospheric humidity and rain normally experienced in exterior environments. |
| THEORETICAL COVERAGE | A guide to the theoretical coverage which can be achieved under normal conditions is 14m ² /L |
| COMPOSITION (nominal) | Pigment: Lightfast Non-Lead Pigments Binder: Modified Alkyd Solvent: White spirit. |
| VOLUME SOLIDS | 38% (nominal) |
| FLASH POINT | 38-55°C |
| DRYING TIME | Single coat at standard thickness: |
| Touch Dry | 1-2Hours |
| Recoat | 4 hours |
| FILM THICKNESS | Wet: 50 micro-meters Dry: 20 micro-meters |
| SURFACE PREPARATIONS | Surfaces must be clean, dry, free from all defective or poorly adhering material, dirt, grease wax etc. All surfaces should be thoroughly rubbed down in the direction of the grain, using a suitable abrasive paper and then dusted off. |

APPLICATION

Brush & Roller

**THINNING**

Brush or Roller

For sealing new or bare surfaces, thin up to 1 part of Mineral Turpentine to 5 parts of paint (20%).
For normal use, thinning is usually not necessary

STIR

Stir paint in a circular lifting motion to mix well before use

SPRAY RECOMMENDATIONS

Conventional Spray

Satisfactory through most equipment.

Airless Spray

A typical set up for airless spray application would be a minimum working pressure on paint of 140 kg/cm² (2000 lb./sq. in) with a spray tip size 0.38mm (13 thou) and a spray tip angle of 65°.

CLEAN UP

Clean all equipment with Mineral turpentine immediately after use.

MAINTENANCE

To remove oil or grease from coated surface use degreaser. For most spillages simply clean with detergent and hose or mop away with fresh water.

SYSTEM INFORMATION**PRIMER/ SEALER/UNDERCOAT****FINISH (2 COATS)**

Clearproof Sanding Sealer

Clearproof Exterior Clear Finish

SAFETY HEALTH AND ENVIRONMENT INFORMATION

Refer Safety Data Sheet -available for use on request

Any advice, recommendations, information, assistance or service provided by AkzoNobel Paints in relation to goods manufactured or marketed by it or their use or any application is given in good faith. However, any advice, recommendations, information, assistance or service provided by AkzoNobel Paints is provided without expressed or implied warranties. For further information or if you have any concerns about using this product, kindly contact:

Attn: Stephen Woodcock

AkzoNobel (PNG) Ltd,
P O Box 1264,
Tel.: +675 7192 1001/02/03, Fax: +675 7031 8440/8441
Vakari Street, Gerehu Stage 6, Port Moresby,
Papua New Guinea

Emergency Contact: +675 7192 1000 (24 hr.)
Fire Ambulance: 110 or 000 (PNG)