



Taubmans Easycoat Flat

PRODUCT NAME	Taubmans Easycoat Flat
VARIANT NAME	FLAT
DESCRIPTION	Taubmans Easycoat Flat is a premium quality flat washable paint that is ideal for ceilings or areas which have imperfections.
USAGE	Taubmans Easycoat Flat is suitable for use on ceilings and Interior walls. Suitable for use on timber or wood surfaces
BENEFITS	Clean common household stains off your wall easily Tough resilient surface that is washable Colour guard Technology to lock colours in. Low Odour and VOC Lead-free; non toxic
PACK SIZE	1, 5, 18 Litres
COLOUR RANGE	Refer to Taubmans Colour Offer
FILM PROPERTIES Water Resistance	Will tolerate the levels of atmospheric humidity present in normal interior environments and will withstand moderately vigorous washing.
THEORETICAL COVERAGE	A guide to the theoretical coverage which can be achieved under normal conditions are 10-11 m2/liter.
COMPOSITION (nominal)	Pigment: Lightfast Non-Lead Pigments and Mineral Extenders. Binder: PVA Copolymer Emulsion. Solvent: Water.
VOLUME SOLIDS	White 42% (nominal), other colours will vary.
FLASH POINT	Non-Flash
DRYING TIME	Single coat at standard thickness: Touch Dry Dependent on temperature and humidity. Recoat 1-2 hours. Allow 4 hours in cold or humid areas
FILM THICKNESS	<30µm
SURFACE PREPARATIONS	Surfaces must be sound, clean, dry and free from all defective or poorly adhering material, dirt, grease or wax and be thoroughly rubbed down using a suitable abrasive paper and dusted off. If after thorough preparation, surfaces remain powdery, seal with one coat of an appropriate Primer (see below).

APPLICATION

Brush & Roller

**THINNING**

For sealing new or bare surfaces thin with up to 1 part of clean water to 5 parts of paint (20%).

Brush or Roller

For normal use, thinning is usually not necessary. If required, should not exceed 1 part of clean water to 10 parts of paint (10%).

Conventional Spray

Add up to 1 part of clean water to 5 parts of paint (20%).

Airless Spray

Ready for use.

STIR

Stir paint in a circular lifting motion to mix well before use

SPRAY RECOMMENDATIONS

Satisfactory through most equipment.

Conventional Spray

A typical set up for airless spray application would be a minimum working pressure on paint of 140 kg/cm² (2000 lb./sq. in) with a spray tip size 0.58mm (23 thou) and a spray tip angle 65°

Airless Spray

CLEAN UP

Clean all equipment with clean water immediately after use.

MAINTENANCE

To remove oil or grease from coated surface use degreaser. Do not use thinners, paint stripper or other aggressive solvents as they will be detrimental to this coating. For most spillages simply clean with detergent and hose or mop away with fresh water.

SYSTEM INFORMATION

UNDERCOAT (1 COAT)

FINISH (2 COATS)

Plaster Board

Ultra Kote Oil Base Undercoat
Ultra Kote Acrylic Sealer Undercoat

Taubmans Easycoat Flat

Masonry

Ultra Kote Oil Base Undercoat
Ultra Kote Acrylic Sealer Undercoat

Taubmans Easycoat Flat

Taubmans Easycoat Flat

Previously Painted Surface

Ultra Kote Oil Base Undercoat
Ultra Kote Acrylic Sealer Undercoat

SAFETY HEALTH AND ENVIRONMENT INFORMATION

Refer Safety Data Sheet -available for use on request

Any advice, recommendations, information, assistance or service provided by AkzoNobel Paints in relation to goods manufactured or marketed by it or their use or any application is given in good faith. However, any advice, recommendations, information, assistance or service provided by AkzoNobel Paints is provided without expressed or implied warranties. For further information or if you have any concerns about using this product, kindly contact:

Attn: Stephen Woodcock

AkzoNobel (PNG) Ltd,
P O Box 1264,
Tel.: +675 7192 1001/02/03, Fax: +675 7031 8440/8441
Vakari Street, Gerehu Stage 6, Port Moresby, Papua New Guinea

Emergency Contact: +675 7192 1000 (24 hr.)
Fire Ambulance: 110 or 000 (PNG)