


Rustproof Roof and Metal Silver Enamel

PRODUCT NAME	Rustproof Roof and Metal Silver Enamel
CODE	RPROOF
DESCRIPTION	Taubmans Rustproof Roof and Metal Silver Enamel is a high quality solvent-based paint.
USAGE	Suitable for use on all types of interior and exterior metal surfaces. It is ideal for use on heated surfaces up to 260°C
BENEFITS	Gives an exceptionally bright lustre with excellent durability
PACK SIZE	1 & 5 Litres Only
COLOUR RANGE	Silver
FILM PROPERTIES	
Chemical Resistance	Resistant to mild chemical fume attack but where there is heavy attack, e.g. actual contact with chemicals, specialist paint systems may be required.
Heat resistance	Generally resistant to heat up to 260°C.
Water Resistance	Resistant to the levels of atmospheric humidity present in normal interior and exterior environments and will withstand repeated washing. Not suitable for use on immersed surfaces.
THEORETICAL COVERAGE	A guide to the theoretical coverage which can be achieved under normal conditions is 12 m ² /L.
COMPOSITION (nominal)	
	Pigment: Leafing Aluminium.
	Binder: Alkyd.
	Solvent: White Spirit.
VOLUME SOLIDS	60% (nominal).
FLASH POINT	23-<32 °C.
DRYING TIME	Single coat at standard thickness:
Touch Dry	2-4 hours.
Recoat	5-6 hours.
FILM THICKNESS	Wet: 50 micro-metres. Dry: 30 micro-metres.
SURFACE PREPARATIONS	<p>New Surfaces generally must be clean, dry, free from all defective or poorly adhering material, dirt, grease, wax etc.</p> <p>Previously painted surfaces should be thoroughly rubbed down using a suitable abrasive paper and then dusted off.</p> <p>Steel surfaces should be manually prepared by power or hand tool.</p> <p>For optimum performance new galvanized and aluminium surfaces should be cleaned and degreased, then pre-treated with an appropriate pre-treatment primer to ensure good adhesion.</p>
APPLICATION	Brush & Roller 

THINNING Ready for use, thinning is usually not necessary.
Brush or Roller
Conventional Spray Add up to 1 part of Mineral Turpentine to 10 parts of paint (10%).

STIR Stir paint in a circular lifting motion to mix well before use

SPRAY RECOMMENDATIONS Satisfactory through most equipment.
Conventional Spray

CLEAN UP Clean all equipment with **Mineral Turpentine** immediately after use.

MAINTENANCE To remove oil or grease from coated surface use degreaser. When spillages occur, use Mineral Turpentine immediately to clean up.

SYSTEM INFORMATION	Primer	Undercoat	FINISH (2 COATS)
Ferrous Metal (Steel heated up to 90°C)	Prepright Grey Green Primer	Prepright Traditional Undercoat	Rustproof Roof & Metal Silver Enamel
Galvanized Metal (Steel heated up to 260°C)	Rustproof Roof & Metal Silver Enamel	NA	Rustproof Roof & Metal Silver Enamel

SAFETY HEALTH AND ENVIRONMENT INFORMATION Refer Safety Data Sheet -available for use on request

Any advice, recommendations, information, assistance or service provided by AkzoNobel Paints in relation to goods manufactured or marketed by it or their use or any application is given in good faith. However, any advice, recommendations, information, assistance or service provided by AkzoNobel Paints is provided without expressed or implied warranties. For further information or if you have any concerns about using this product, kindly contact:

Attn: Stephen Woodcock

AkzoNobel (PNG) Ltd,
P O Box 1264,
Tel.: +675 7192 1001/02/03, Fax: +675 7031 8440/8441
Vakari Street, Gerehu Stage 6, Port Moresby,
Papua New Guinea

Emergency Contact: +675 7192 1000 (24 hr.)
Fire Ambulance: 110 or 000 (PNG)