

Sunproof Max Gloss

PRODUCT NAME	Sunproof Max
VARIANT NAME	Gloss
DESCRIPTION	A premium top quality 100% acrylic based emulsion paint. Sunproof Max has excellent durability and colour fastness.
USAGE	Sunproof Max is suitable on new or previously painted masonry surfaces such as brickwork, plaster, cement, rendering and galvanise steel.
BENEFITS	<p>Excellent Alkali Resistance and Adhesion properties Great Durability and Colour Fastness. Colour Lock Technology to ensure Colour Stays New Longer Protection against Fungus & Algae Dirt Resistance Enables paint to stay cleaner and brighter Low Odour even when freshly painted Five (5) year Guarantee</p>
PACK SIZE	1, 5, 18 Litres
COLOUR RANGE	Refer to Taubmans Colour Collaterals
FILM PROPERTIES	Resistant to mild atmospheric fume attack and to the salts in new mortar, rendering and similar surfaces.
Chemical Resistance	
Water Resistance	Resistant to the level of atmospheric humidity normally experienced in exterior environment
THEORETICAL COVERAGE	9-10m ² /Lt (Coverage will be lower on rough or absorbent surfaces)
COMPOSITION (nominal)	<p>Pigment: Lightfast Non-Lead Pigments and Mineral Extenders. Binder: Acrylic Emulsion. Solvent: Water.</p>
VOLUME SOLIDS	White 40% (nominal), other colors will vary
FLASH POINT	Non-Flash
DRYING TIME	30 minutes
Touch Dry	2 hours at 25°C (Allow 4 hours in cold or humid areas.)
Recoat	
FILM THICKNESS	<20µm
SURFACE PREPARATIONS	<p>New Work Surfaces must be sound, clean, dry and free from grease, wax or any loose material that prevents good adhesion. Rub down using a suitable abrasive paper and dust off. For masonry surface, the relative humidity should be under 17% according to Protimeter or let the substrate dry from 21-28 days in normal conditions (average temperature 30°C, humidity of environment is about 80%)</p> <p>Previously Painted Surface Remove all loose and flaking paint by scraping or sanding previously painted areas and sand smooth. Surface must be free of any loose material that prevents good</p>

adhesion. Seal with one coat of appropriate primer. If mould is present, treat with suitable fungicidal wash or diluted bleach and rinse with clean water. Allow to dry before painting.

For Galvanised Steel Surface

Degrease new galvanised steel and abrade structural galv to remove chemical treatments to ensure maximum adhesion. Prime with Taubmans 3 in 1 for better intercoat adhesion.

APPLICATION

Brush & Roller



THINNING

Brush or Roller

For normal use, thinning is usually not necessary. If required dilute with 10% clean water and stir well before use.

STIR

Stir paint in a circular lifting motion to mix well before use

SPRAY RECOMMENDATIONS

Conventional Spray

Satisfactory through most equipment.

Airless Spray

A typical set up for airless spray application would be a minimum working pressure on paint of 140 kg/cm² (2000 lb./sq. in) with a spray tip size 0.58mm (23 thou) and a spray tip angle 65°.

CLEAN UP

Clean all equipment with clean water immediately after use.

MAINTENANCE

To remove oil or grease from coated surface use degreaser. For most spillages simply clean with detergent and hose or mop away with fresh water.

SYSTEM INFORMATION

	Primer/ Sealer/Undercoat	FINISH (2 COATS)
Plaster Board	Taubmans 3 in 1	Sunproof Max Gloss
Masonry	Taubmans 3 in 1	Sunproof Max Gloss
Previously Painted Surface	Taubmans 3 in 1	Sunproof Max Gloss
Galvanised Steel	Taubmans 3 in 1	Sunproof Max Gloss

SAFETY HEALTH AND ENVIRONMENT INFORMATION

Refer Safety Data Sheet -available for use on request

Any advice, recommendations, information, assistance or service provided by AkzoNobel Paints in relation to goods manufactured or marketed by it or their use or any application is given in good faith. However, any advice, recommendations, information, assistance or service provided by AkzoNobel Paints is provided without expressed or implied warranties. For further information or if you have any concerns about using this product, kindly contact:

Attn: Stephen Woodcock

Emergency Contact: +675 7192 1000 (24 hr.)
Fire Ambulance: 110 or 000 (PNG)

AkzoNobel (PNG) Ltd,
P O Box 1264,
Tel.: +675 7192 1001/02/03, Fax: +675 7031 8440/8441
Vakari Street, Gerehu Stage 6, Port Moresby,
Papua New Guinea