

Ultra-Kote Acrylic Sealer Undercoat

PRODUCT NAME	Ultra-Kote Acrylic Sealer Undercoat
CODE	ULKPSU
DESCRIPTION	Ultra Kote Acrylic Sealer Undercoat is a good quality, water-based sealer
USAGE	Ultra Kote Acrylic Sealer Undercoat is suitable for interior and exterior masonry surface such as brickwork, plaster and cement. It is suitable for use on both new and previously painted surfaces
BENEFITS	The special acrylic emulsion ensures excellent alkali resistance. The high content of this emulsion minimizes the risk of efflorescence and seals off the substrate. Fast Drying Lead-free: non toxic
PACK SIZE	5, 18 Litres
COLOUR RANGE	Refer to Ultra-Kote Colour Range
FILM PROPERTIES Water Resistance	Will tolerate a slightly damp surface but is not suitable where the surface is saturated
THEORETICAL COVERAGE	A guide to the theoretical coverage which can be achieved under normal conditions is 10.5-11.5 m ² /litre Coverage will be lower on rough or absorbent surfaces.
COMPOSITION (nominal)	Pigment: Lightfast Non-Lead Pigments and Mineral Extenders. Binder: Acrylic Emulsion. Solvent: Water.
VOLUME SOLIDS	White 45% (nominal)
FLASH POINT	Non-Flash
DRYING TIME	Single coat at standard thickness: Touch Dry Dependant on temperature and humidity. Recoat 1-2 hours.(Allow 4 hours in cold or humid areas).
FILM THICKNESS	<20µm
SURFACE PREPARATIONS	Surfaces must be sound, clean, dry and free from all defective or poorly adhering material, dirt, grease or wax and be thoroughly rubbed down using a suitable abrasive paper and dusted off. Treat areas affected by mould, fungi or algae with Sugar Soap. If after thorough preparation, surfaces remain powdery, seal with one coat of an appropriate Primer (see below).
APPLICATION	Brush & Roller 

THINNING

Brush or Roller For sealing new or bare surfaces thin with up to 1 part of clean water to 10 parts of paint (10%). For normal use, thinning is usually not necessary.

Conventional spray Add up to 1 part of clean water to 10 parts of paint (10%).
Ready for use.

STIR

Stir paint in a circular lifting motion to mix well before use

SPRAY RECOMMENDATIONS

Conventional Spray Satisfactory through most equipment

Airless Spray A typical set up for airless spray application would be a minimum working pressure on paint of 140 kg/cm² (2000 lb/sq in) with a spray tip size 0.43mm (17 thou) and a spray tip angle 65°.

CLEAN UP

Clean all equipment with clean water immediately after use.

MAINTENANCE

To remove oil or grease from coated surface use degreaser. For most spillages simply clean with detergent and hose or mop away with fresh water.

SYSTEM INFORMATION

Primer/ Sealer/Undercoat

FINISH (2 COATS)

Plaster Board

Ultra-Kote Acrylic Sealer Undercoat

Ultra Kote Exterior Gloss Acrylic
Ultra-Kote Interior Semi-Gloss Acrylic

Masonry

Ultra Kote Acrylic Sealer Undercoat

Ultra Kote Exterior Gloss Acrylic
Ultra-Kote Interior Semi-Gloss

Previously Painted Surface

Ultra Kote Acrylic Sealer Undercoat

Ultra Kote Exterior Gloss Acrylic
Ultra-Kote Interior Semi-Gloss Acrylic

SAFETY HEALTH AND ENVIRONMENT INFORMATION

Refer Safety Data Sheet -available for use on request

Any advice, recommendations, information, assistance or service provided by AkzoNobel Paints in relation to goods manufactured or marketed by it or their use or any application is given in good faith. However, any advice, recommendations, information, assistance or service provided by AkzoNobel Paints is provided without expressed or implied warranties. For further information or if you have any concerns about using this product, kindly contact:

Attn: Stephen Woodcock

AkzoNobel (PNG) Ltd,
P O Box 1264,
Tel.: +675 7192 1001/02/03, Fax: +675 7031 8440/8441
Vakari Street, Gerehu Stage 6, Port Moresby,
Papua New Guinea

Emergency Contact: +675 7192 1000 (24 hr.)
Fire Ambulance: 110 or 000 (PNG)