



สีรองพื้นปูนใหม่กันต่าง ดูลักซ์ เวเธอร์ชิลด์ ชูเปอร์ไพร์เมอร์ เป็นสีรองพื้นปูนเสริมประสิทธิภาพ ด้วยสูตร ดับเบิ้ล แอ็คชั่นกันต่างและเพิ่มการยึดเกาะ ทำจากอะครีลิค ที่มีส่วนผสมของ นาโน แอคทีฟ จึงทำให้โมเลกุลฟิล์มสีมีความละเอียดเป็นพิเศษ แทรกซึมสู่ผนังปูนได้ลึกและมากกว่า จึงทำให้ต้านฤทธิ์ต่างเกลือจากผนังปูนได้ดีเยี่ยม อีกทั้งยังเกิดผ่นเงาได้แน่นอน จึงช่วยยืดอายุของฟิล์มสี ไม่ให้หลุดล่อนง่าย ไม่มีส่วนผสมของสารปรอทและตะกั่ว

### คำแนะนำเพิ่มเติม

เพื่อเพิ่มประสิทธิภาพสูงสุดในการปกป้อง ควรใช้คู่กับผลิตภัณฑ์ดูลักซ์ เวเธอร์ชิลด์อื่นๆ ตามขั้นตอนของระบบการทาสี

- น้ำยากำจัดและยับยั้งเชื้อราและตะไคร่น้ำ ดูลักซ์ เวเธอร์ชิลด์ โมลด์วอช
- สีทาพื้นหน้าสำหรับภายนอก ดูลักซ์ เวเธอร์ชิลด์ พาวเวอร์เฟล็กซ์ หรือ ดูลักซ์ เวเธอร์ชิลด์ ไฮโดรเฟรช หรือ ดูลักซ์ เวเธอร์ชิลด์ อัลติมา

### ข้อมูลทางเทคนิคและคุณสมบัติของฟิล์มสี

ประเภทสี	สีรองพื้นปูน อะครีลิค
ลักษณะฟิล์มสี	ด้าน
ขนาดบรรจุ	1 และ 5 ยูเอสแกลลอน .9 ลิตร
เจดสี	ขาวอมเหลือง
เนื้อสีโดยปริมาตร	ประมาณ 35%
ระยะเวลาแห้งสัมผัส	อย่างน้อย 30 นาที
ระยะเวลาทาทับ	30 นาที - 2 ชั่วโมง
การครอบคลุมพื้นที่ตามทฤษฎี	35-40 ตร.ม. / เทียว / ยูเอสแกลลอน

\*พื้นที่ครอบคลุมเป็นค่าทางทฤษฎี อาจแตกต่างจากการใช้งานจริงไม่เกิน 20%

### วิธีการใช้งาน

วิธีการใช้งาน	ทาด้วยแปรง ลูกกลิ้ง หรือสเปรย์
การผสมเฉื่อยจาง	น้ำสะอาด
การผสมก่อนใช้งาน	เติมน้ำสะอาด 1 ส่วน ต่อสี 10 ส่วน (10%)

### ระบบการทาสี

- ขั้นที่ 1 การเตรียมพื้นผิว**
- ทิ้งพื้นปูนแห้งสนิทอย่างน้อย 1 เดือนหลังจากฉาบปูน ก่อนทาสีทุกครั้งต้องล้างทำความสะอาดพื้นผิวให้ปราศจากฝุ่นละออง เศษซีเมนต์ คราบไขมันและสิ่งสกปรกต่างๆ หรืออาจใช้กระดาษทรายขัดฝุ่นออกให้หมดก่อนซ่อมแซมตกแต่งรอยแตกร้าวบนพื้นผิวด้วยสีเบ็ดดูลักซ์ อะครีลิคฟิลเลอร์ 1040 ชัดแต่งให้เรียบ
- ขั้นที่ 2 การทาสีรองพื้น**
- ทาสีรองพื้นปูนใหม่กันต่าง ดูลักซ์ เวเธอร์ชิลด์ ชูเปอร์ไพร์เมอร์ จำนวน 1 เทียว ทิ้งให้แห้งอย่างน้อย 30 นาที - 2 ชั่วโมง ก่อนทาสีทับหน้า
- ขั้นที่ 3 การทาสีทับหน้า**
- ทาสีทับหน้าด้วยผลิตภัณฑ์ดูลักซ์ เวเธอร์ชิลด์ สำหรับทาภายนอก อย่างน้อย 2 เทียว โดยทิ้งระยะให้สีที่ทาชั้นแรกแห้งสนิทอย่างน้อย ประมาณ 30 นาที - 2 ชั่วโมง ก่อนทาสีทับชั้นถัดไป



ISO 9001 QMS03026/630  
ISO 14001 EMS05021/198  
OHSAS 18001 OHSAS04016/079  
TIS 18001 OHS01013/028



# Dulux Weathershield SuperPrimer Acrylic Primer for Exterior



Dulux Weathershield Superprimer is acrylic water borne primer sealer with Double Action formulation for excellent alkali and fungus resistance. Made of acrylic with fine particle of Nano Active for better penetration and adhesion for longer life of paint film. Contains no added lead and no added mercury.

## ADDITION NOTE

- For perfect result, use in conjunction with other Dulux Weathershield products throughout paint system.
- Dulux Weathershield Mould Wash
  - Dulux Weathershield Powerflex or Dulux Weathershield Hydrofresh or Dulux Weathershield Ultima

## Technical Information & Paint Film Properties

Type of Paint	Acrylic Primer
Finish	Matt
Pack size	1 and 5 U.S. Gallons, 9 Litres
Colour Offer	Cream
Volume Solids	35%
Touch Dry	At least 30 Minutes
Recoat Dry	30 Minutes - 2 Hours
Theoretical Coverage	35-40 Sq.m./coat/gallon

\*Coverage is theoretical value and may differ from real application +-20%

## Application

Application Method	Brush, Roller or Spray
Thinning	Clean Water
Dilution	Add up to 1 part of clean water to 10 part of paint (10%)

## Application System

<b>Step 1: Surface Preparation</b>	Leave surface dry for at least 1 month. Surfaces must be dry, clean and free from dirt and loose materials. Repair all cracks with Dulux Acrylic Filler 1O4O. All surfaces must be sealed and prevented water to leak to the paint film bubble or peeling.
<b>Step 2: Priming</b>	Apply 1 coat of Dulux Weathershield SuperPrimer. Allow at least 30 minutes-2 hours drying before applying top coat.
<b>Step 3: Topcoat</b>	Apply at least 2 coats of any Dulux Weathershield exterior paints. Allow at least 30 minutes - 2 hours drying before applying top coat.



ISO 9001 QMS03026/630  
ISO 14001 EMS05021/198  
OHSAS 18001 OHSAS04016/079  
TIS 18001 OHS01013/028

The information in this datasheet is given to the best of our knowledge based on laboratory testing and for use recommendation. As the product is often used under conditions beyond our control, the company cannot guarantee anything only the quality of the product.

AkzoNobel Paints (Thailand) Ltd. (Former ICI Paints (Thailand) Ltd.) 34/5 Moo 1 Chaeng Watana Road, Klongklue, Pakkred Nonthaburi 11120  
Customer Service : Telephone (662) 572-8888 Fax (662) 572-8889, www.dulux.co.th, www.facebook.com/duluxthailand