



Issued 08/21

1022

# WEATHERSHIELD QUICK DRY EXTERIOR HIGH GLOSS

## Part 3 of a 3-part weather-resistant and quick-drying paint system for exterior trim and woodwork.

This water-based formulation has excellent flow and levelling for a smooth high gloss finish. Specially developed to give exterior woodwork extensive protection for up to 8 years\*. It offers great flexibility to accommodate the natural movement of wood that occurs over time. It contains a fungicide to inhibit mould growth within the paint film and help it stay cleaner for longer, reducing maintenance cycles.

Proven to be as durable as a solvent based equivalent.

\*if correctly applied as per instructions for use.

### KEY BENEFITS

- 8 Year All Weather Protection
- Flexible Formulation
- Smooth High Gloss Finish
- Stays Cleaner for Longer
- Coverage up to 13m<sup>2</sup> per litre

### PRODUCT INFORMATION

#### Typical Use

Ideal for use on exterior trim and woodwork.

#### Pack Size

1L, 2.5L and 5L.

#### Colour Range

PBW, light, medium and extra deep bases available.

See appropriate **Dulux Trade** colour literature or visit [duluxtrade.co.uk](http://duluxtrade.co.uk).

#### Composition (nominal)

**Pigment:** Non Lead Pigments.

**Binder:** Alkyd Emulsion.

**Solvent:** Water.

#### Volume Solids

39% (nominal).

### SURFACE PREPARATION

To get the best results, ensure surfaces to be painted are sound, clean and dry (new surfaces particularly must be fully dry) and free from all defective or poorly adhering material such as dirt, grease or wax.

Thoroughly rub down previously painted surfaces, using 'wet flattening' methods where possible, then wipe off with a damp, lint free cloth. Special precautions should be taken during surface preparation of pre-1960s paint surfaces over wood and metal as they may contain harmful lead.

Treat any knots in wood with an appropriate knotting solution. Any surface defects should be filled with the

appropriate **Polycell Trade Polyfilla**.

Prime any bare metal with 1 coat of **Dulux Trade Metalshield Zinc Phosphate Primer**.

When painting areas such as plastic rainwater goods, **Weathershield Quick Dry Exterior Gloss** can be used. Apply 1 coat of **Weathershield Quick Dry Flexible Undercoat**. Followed by 1 coat of **Weathershield Quick Dry Exterior High Gloss** thinned to 1 part water to 10 parts paint direct to the surface.



Issued 08/21

1022

# WEATHERSHIELD QUICK DRY EXTERIOR HIGH GLOSS

New joinery is often factory primed using a stain basecoat (also called a dual-purpose primer). These materials quickly erode when left exposed and may need to be re-primed.

## SYSTEMS INFORMATION

STIR THOROUGHLY BEFORE USE.

Prime all bare wood with 2 coats of Weathershield Preservative Primer (to be used on softwood only) followed by 2 coats of the appropriate coloured Weathershield Quick Dry Flexible Undercoat.

Finish with 2 coats of Weathershield Quick Dry Exterior High Gloss.

Where a special process colour is to be used or a strong colour change is required, additional coats may be needed (see appropriate Dulux Trade colour card).

Allow a minimum of 4 hours before overcoating Weathershield Quick Dry Flexible Undercoat.

Allow a minimum of 4 hours before applying a second coat of Weathershield Quick Dry Exterior High Gloss.

When using darker colours, the final appearance will be visible once dry. The paint will look lighter when applied and while still wet.

## APPLICATION METHOD

Brush, roller or spray.

Do not use below 10°C, immediately after rain, fog or frost, or when these conditions are forecast.

## Practical Coverage

A guide to the practical coverage which can be achieved under normal conditions is up to 13m<sup>2</sup> per litre.

## Spray Recommendations

### **Airless Spray:**

Use a 308 Fine Finish tip.

Pressure: approx. 1200 psi.

No thinning.

The above settings are an indication only and will vary with equipment. To get the best results, it is advised to tune the settings to suit the site conditions and should be assessed by means of a test area.

## Drying Times

*Single coat at standard thickness:*

**Touch Dry:** 1-2 hours dependent upon temperature and humidity.

**Recoat:** 4-6 hours dependent upon temperature and humidity.

## Cleaning Up

After use, remove as much product as possible from equipment before cleaning with water.

When this paint container is empty please ask your stockist about recycling. If you have leftover paint, please dispose of it responsibly and consider donating it to **Community RePaint**.

Find out more at

***[www.duluxtradepaintexpert.co.uk/products/sustainability](http://www.duluxtradepaintexpert.co.uk/products/sustainability)***



Issued 08/21

1022

# WEATHERSHIELD QUICK DRY EXTERIOR HIGH GLOSS

## Transportation & Storage

Do not use or store in extremes of temperature and protect from frost. To prevent spillage, please store and transport upright.

## VOC

EU limit value for this product (cat.: A/d): 130g/l (2010). This product contains max. 45g/l VOC.  
VOC content: Low (0.30-7.99%).

## FURTHER SUPPORT

If you need further support, please contact the **AkzoNobel** Technical Advice Centre on 0333 222 70 70.

\* **Weathershield** Preservative Primer contains 3-iodo-2-propynyl-n-butyl carbamate and propiconazole.  
*Use biocides safely. Always read the label and product information before use.*

*Always read full Health, Safety & Environmental Information on can before use.*

Safety datasheet (SDS 1022) is available free on request by telephoning the **AkzoNobel** Technical Advice Centre or by visiting [duluxtrade.co.uk](http://duluxtrade.co.uk).

AkzoNobel, the AkzoNobel logo, the Flourish logo, Dulux Trade, Weathershield, Polycell, Polyfilla, Community RePaint and the Planet Possible logo are trademarks of the AkzoNobel group. © AkzoNobel 2021.

