


SADOLIN DULUX EASYCLEAN SILK



Product Name	Sadolin Dulux EasyClean Silk
Description and Usage	<p>Sadolin Dulux EasyClean Silk is a premium quality washable acrylic paint for use on all interior walls where a subtle, elegant silk finish is required. It has the advantages of unmatched stain resistance and outstanding scrubability combined with low odour, non-yellowing, easy application and water clean-up.</p> <p>Sadolin Dulux EasyClean Silk is suitable on new or previously painted masonry surfaces such as brickwork, plaster, cement, rendering and semi-permanent interior finishes.</p>
Benefits	<ul style="list-style-type: none"> • KidProof Technology, tough stain repellent • Anti-bacterial property • Washable & easy cleaning • Outstanding scrub resistance • Long lasting & brighter colours • Low VOC & low odour • No added lead & mercury
Pack Size	<p>1 & 4 Litre: Base W, Base A, Base B, Base C, Base D</p> <p>16.5 Litre: Base W, Base A, Base B; 17 Litre: Base C, Base D</p>
Colour Range	See appropriate Colour Card
Film Properties	
<i>Water Resistance</i>	Resistant to the levels of atmospheric humidity normally experienced in interior environment.
Composition (nominal)	<p>Pigment : Lightfast Non-lead Pigments</p> <p>Binder : Acrylic Emulsion</p> <p>Solvent : Water</p>
Volume Solids	White 40%, other colours will vary
Drying Times	Single coat at standard thickness:
<i>Touch Dry</i>	Dependent on temperature and humidity
<i>Recoat</i>	2 – 4 hours
Film Thickness	30 – 36 microns dry film thickness
Theoretical Coverage	The spreading capacity of this product will vary considerably according to the roughness and porosity of the surface. On smooth surfaces of average porosity 11 – 12 m ² /litre.

Application



SADOLIN DULUX EASYCLEAN SILK



Thinning					
<i>Brush or Roller</i>	For normal use thinning is not usually necessary, but if required add up to 1 part of clean water to 10 parts of paint (10%).				
<i>Conventional Spray</i>	For normal use thinning is not usually necessary, but if required add up to 1 part of clean water to 3 parts of paint (30%).				
<i>Airless Spray</i>	Ready for use. Thinning is usually not required.				
Spray Recommendations					
<i>Conventional Spray</i>	Satisfactory through most equipment.				
<i>Airless Spray</i>	A typical set up for airless spray application would be a minimum working pressure on paint of 140 kg/cm ² with a spray tip size 0.58mm and a spray tip angle 65°.				
Cleaning Up					
Clean all equipment with clean water immediately after use.					
Surface Preparation					
Surface must be sound, clean, dry and free from all defective or poorly adhering material, dirt, grease or wax and be rubbed down using a suitable abrasive paper and dusted off. Treat areas affected by fungi or algae with Fungicidal Wash. If surfaces remain powdery or suffer from alkali attack after thorough preparation, seal with one coat of an appropriate sealer.					
System Information					
<i>Powdery and Alkaline Surfaces</i>	<table border="0"> <tr> <td>Sealer (1 coat)</td> <td>Finish (2 coats)</td> </tr> <tr> <td>Sadolin Dulux Interior Primer SB</td> <td>Sadolin Dulux EasyClean Silk</td> </tr> </table>	Sealer (1 coat)	Finish (2 coats)	Sadolin Dulux Interior Primer SB	Sadolin Dulux EasyClean Silk
Sealer (1 coat)	Finish (2 coats)				
Sadolin Dulux Interior Primer SB	Sadolin Dulux EasyClean Silk				
<i>New, Normal, Sound Surfaces</i>	Sadolin Dulux Interior Super Primer WB				
Health, Safety and Environment Information					
Product Safety Data Sheet available upon request.					

For further information or if you have any concerns about using this product, contact us at:

Akzo Nobel Oman SAOC
P.O. Box 531, Ruwi, Postal code 112
Sultanate of Oman
Tel: (968) 24446218 Fax: (968) 24446962
Email: sadolin.dulux@akzonobel.com
Website: www.sadolindulux.com

Any advice recommendations, information, assistance or service provided by AkzoNobel Paints in relation to goods manufactured or marketed by it or their use or any application is given in good faith. However, advice, recommendations, information, assistance or service provided by AkzoNobel Paints is provided without expressed or implied warranties.