

SADOLIN DULUX INSPIRE SADOMASTIC SILK



Product Name	Sadolin Dulux Inspire Sadomastic Silk
Description and Usage	<p>Sadolin Dulux Inspire Sadomastic Silk is high quality water-based emulsion paint for both new and (appropriately primed) previously painted interior masonry surfaces. It is specially formulated for durability and longer lasting colour.</p> <p>Sadolin Dulux Inspire Sadomastic Silk is suitable on new or previously painted masonry surfaces such as brickwork, plaster, cement, rendering and semi-permanent interior finishes.</p>
Benefits	<ul style="list-style-type: none"> • Long lasting colour • Good coverage • Low odour and VOC
Pack Size	<p>1 & 4 Litre: Base W, Base A, Base B, Base C, Base D</p> <p>16.5 Litre: Base W, Base A, Base B; 17 Litre: Base C, Base D</p>
Colour Range	See appropriate Colour Card
Film Properties	
<i>Water Resistance</i>	Resistant to the levels of atmospheric humidity normally experienced in interior environment.
Composition (nominal)	<p>Pigment : Non-lead Pigments</p> <p>Binder : Styrene-Acrylic Emulsion</p> <p>Solvent : Water</p>
Volume Solids	White 35 % ± 2, other colours will vary
Drying Times	Single coat at standard thickness:
<i>Touch Dry</i>	Dependent on temperature and humidity
<i>Recoat</i>	1 - 2 hours
Film Thickness	30 – 40 microns dry film thickness
Theoretical Coverage	The spreading capacity of this product will vary considerably according to the roughness and porosity of the surface. On smooth surfaces of average porosity 9 – 12 m ² /litre/coat.
Application	
Thinning	
<i>Brush or Roller</i>	For normal use thinning is not usually necessary, but if required add up to 1 part of clean water to 10 parts of paint (10%).
<i>Conventional Spray</i>	For normal use thinning is not usually necessary, but if required add up to 1 part

SADOLIN DULUX INSPIRE SADOMASTIC SILK



Airless Spray

of clean water to 3 parts of paint (30%).
Ready for use. Thinning is usually not required.

Surface Preparation

Conventional Spray

Satisfactory through most equipment.

Airless Spray

A typical set up for airless spray application would be minimum working pressure on paint of 140 kg/cm² with a spray tip size 0.58 mm and a spray tip angle 65°.

Cleaning Up

Clean all equipment with water immediately after use.

Surface Preparation

Surface must be sound, clean, dry and free from all defective or poorly adhering material, dirt, grease or wax and be rubbed down using a suitable abrasive paper and dusted off. Treat areas affected by fungi and algae with Dulux Fungicidal Wash. If surfaces remain powdery or suffer from alkali attack after thorough preparation, seal with one coat of an appropriate sealer.

System Information

Powdery and Alkaline Surfaces

Sealer (1 coat)

Finish (2 coats)

Sadolin Dulux Interior Primer (SB)

Sadolin Dulux Inspire
Sadomastic Silk

New, Normal, Sound Surfaces

Sadolin Dulux Interior Primer (WB)

Health, Safety and Environment Information

Product Safety Data Sheet available upon request.

For further information or if you have any concerns about using this product, contact us at:

Akzo Nobel Oman SAOC

P.O. Box 531, Ruwi, Postal code 112
Sultanate of Oman
Tel: (968) 24446218 Fax: (968) 24446962
Email: sadolin.dulux@akzonobel.com
Website: www.sadolindulux.com

Any advice recommendations, information, assistance or service provided by AkzoNobel Paints in relation to goods manufactured or marketed by it or their use or any application is given in good faith. However, advice, recommendations, information, assistance or service provided by AkzoNobel Paints is provided without expressed or implied warranties.