

# SADOLIN DULUX INSPIRE SADOMASTIC XT SILK



<b>Product Name</b>	Sadolin Dulux Inspire Sadomastic XT Silk
<b>Description and Usage</b>	<p>Sadolin Dulux Inspire Sadomastic XT Silk is quality paint, formulated based on modified acrylic based emulsion. It is formulated to provide a good protection against fungus and algae growth.</p> <p>Sadolin Dulux Inspire Sadomastic XT Silk is suitable on new or previously painted masonry surfaces such as brickwork, plaster, cement, rendering and semi-permanent exterior finishes.</p>
<b>Benefits</b>	<ul style="list-style-type: none"> <li>• Good adhesion, anti-peeling</li> <li>• Good alkali resistance</li> <li>• Good protection against fungus and algae growth</li> <li>• Good durability and colour fastness</li> </ul>
<b>Pack Size</b>	<p>1 &amp; 4 Litre: Base W, Base A, Base B, Base C, Base D</p> <p>16.5 Litre: Base W, Base A, Base B; 17 Litre: Base C, Base D</p>
<b>Colour Range</b>	See appropriate Colour Card
<b>Film Properties</b>	
<i>Water Resistance</i>	Resistant to the levels of atmospheric humidity normally experienced in exterior environment.
<i>Chemical Resistance</i>	Resistant to mild atmospheric fume attack and to the salts in new mortar, rendering and similar surfaces.
<b>Composition (nominal)</b>	<p>Pigment : Non-lead Pigments</p> <p>Binder : Styrene-Acrylic Emulsion</p> <p>Solvent : Water</p>
<b>Volume Solids</b>	39% ± 2
<b>Drying Times</b>	Single coat at standard thickness:
<i>Touch Dry</i>	Dependent on temperature and humidity
<i>Recoat</i>	1 - 2 hours
<b>Film Thickness</b>	25 – 30 microns dry film thickness
<b>Theoretical Coverage</b>	The spreading capacity of this product will vary considerably according to the roughness and porosity of the surface. On smooth surfaces of average porosity 10 – 12 m <sup>2</sup> /litre/coat.
<b>Application</b>	
<b>Thinning</b>	
<i>Brush or Roller</i>	For normal use thinning is not usually necessary, but if required add up to 1 part of clean water to 10 parts of paint (10%).

# SADOLIN DULUX INSPIRE SADOMASTIC XT SILK



## Conventional Spray

For normal use thinning is not usually necessary, but if required add up to 1 part of clean water to 3 parts of paint (30%).

## Airless Spray

Ready for use. Thinning is usually not required.

## Surface Preparation

### Conventional Spray

Satisfactory through most equipment.

### Airless Spray

A typical set up for airless spray application would be minimum working pressure on paint of 140 kg/cm<sup>2</sup> with a spray tip size 0.58 mm and a spray tip angle 65°.

## Cleaning Up

Clean all equipment with water immediately after use.

## Surface Preparation

Surface must be sound, clean, dry and free from all defective or poorly adhering material, dirt, grease or wax and be rubbed down using a suitable abrasive paper and dusted off. Treat areas affected by fungi and algae with Dulux Fungicidal Wash. If surfaces remain powdery or suffer from alkali attack after thorough preparation, seal with one coat of an appropriate sealer.

## System Information

*Powdery and Alkaline Surfaces*

Sealer (1 coat)

Finish (2 coats)

Sadolin Dulux Exterior Primer (SB)

Sadolin Dulux Inspire  
Sadomastic XT Silk

*New, Normal, Sound Surfaces*

Sadolin Dulux Exterior Primer (WB)

## Health, Safety and Environment Information

Product Safety Data Sheet available upon request.

**For further information or if you have any concerns about using this product, contact us at:**

### Akzo Nobel Oman SAOC

P.O. Box 531, Ruwi, Postal code 112  
Sultanate of Oman  
Tel: (968) 24446218 Fax: (968) 24446962  
Email: sadolin.dulux@akzonobel.com  
Website: www.sadolindulux.com

Any advice recommendations, information, assistance or service provided by AkzoNobel Paints in relation to goods manufactured or marketed by it or their use or any application is given in good faith. However, advice, recommendations, information, assistance or service provided by AkzoNobel Paints is provided without expressed or implied warranties.