

TECHNICAL DATA SHEET

Issue Date: 28/6/2018

1st Edition

ELAFROSTOKOS

Extra Strong Light Weight Putty



DESCRIPTION

Vivechrom Light Weight Putty is ready mixed, extra strong, based on acrylic resin and hollow silica spheres, for filling small and large holes up to 5 cm depth and cracks in one go. Easy applicable and does not loose volume on drying. Accepts nails and screws.

For filling and repairing small and large holes and cracks in most masonry substrates like plaster, brick, stone, concrete and gypsum boards. Interior and exterior use. When used outside two layers of paint are required. Very smooth surface, can be repainted with any paint.

Fills up to 5cm depth in one go

Does not loose volume when dries

Drillable - Holds nails & screws

PRODUCT INFORMATION

Type: Putty based on acrylic resins.

Specific gravity: 0.60 g/ml

VOC: 0 q/L

Application method: Filling knife

Application thickness:

Drying times: 2 hours – 1 day

Drying time depends on weather conditions (humidity, temperature), as well as on type of

surface.

Storage life: 5-35°C









www.vivechrom.gr





ELAFROSTOKOS

Extra Strong Light Weight Putty

SURFACE PREPARATION

- Surfaces must be clean, dry and free from all defective and poorly adhering material, dirt, grease and salts.
- Tub: stir gently to a creamy consistency.
- Touch in nail and screws heads with oil based primer.

APPLICATION

- Can be applied straight from the tub. Knife well into the repair. Smooth level with the surrounding surface, with a wet filling knife, angling surfaces to shed water.
- Replace lid immediately after use. Protect from frost.
- For water based paint a drying time of minimal 2 hours must be held. For solvent based paint a drying time of 1 day is to be held.
- Apply the paint and let it dry at temperatures between 10°C to 35°C.

AFTER USE

Wash tools in warm water immediately after use.

HEALTH, SAFETY & ENVIRONMENTAL INFORMATION

Keep out of reach of children • If medical advice is needed, have product container or label at hand • Do not get in eyes, on skin, or on clothing • Call a POISON CENTER or doctor if you feel unwell • Contains 1, 2-benzisothiazol-3(2H)-one and reaction mass of: 5-chloro-2-methyl-4-isothiazolin-3-one [EC no. 247-500-7] and 2-methyl-2H-isothiazol-3-one (3:1). May produce an allergic reaction • Do not empty into drains • Dispose of contents and container in accordance with all national regulations.

Poison Center: +30210 7793777







FACTORY & HEAD OFFICES: THESI VATHI PIGADI, 19600 MANDRA ATTICA, GREECE TEL.:+30 210 5538700, FAX:+30 210 5550464 THESSALONIKI: ETHN. ANTISTASEOS 114, 55134 KALAMARIA, TEL.:+30 2310 450000, FAX:+30 2310 493984



www.vivechrom.gr