

NEOPAL[®] RELIEF

Decorative textured coating



DESCRIPTION

NEOPAL RELIEF is a decorative textured coating of high durability for interior and exterior use. It is suitable for all new and old surfaces such as plaster, concrete, wood, hardboard. It has outstanding durability to adverse weather conditions and strong adhesion. A big variety of decorative patterns can be created by using special rollers, covering at the same time any minor imperfections of the surface.

For interior and exterior use

Outstanding durability and strong adhesion

Protects and decorates

PRODUCT INFORMATION

Type: Textured coating based on PVA-VEOVA copolymer.

Specific gravity:

Viscosity: 60-70 ps (ROTOTHINNER DIN 51550, 25°C)

Application method: Roller, brush.

Thinning: Ready for use. If needed, is thinned up to 15% with clean water.

Spreading rates: About 1-1,5 m² per kilo per coat on previously prepared surfaces.

Drying times: Touch dry after 2 hours and recoatable after 24 hours. Drying time depends on weather conditions (humidity, temperature)

Colours: It is available in white.

Storage: Store between 5° to 40° C.

VOC (Volatile Organic Compounds)

EU limit value for this product category

A/a Interior matt walls and ceilings (gloss <25@60°): 30 g/l (2010). This product contains max 5 g/l VOC.



www.vivechrom.gr



NEOPAL® RELIEF

Decorative textured coating

SURFACE PREPARATION

- Surfaces must be clean, dry and free from all defective and poorly adhering material, dirt, grease and salts.
- Dry sanding, flame cutting and/or welding of the dry paint film will give rise to dust and/or hazardous fumes. Wet sanding/flatting should be used wherever possible. If exposure cannot be avoided by the provision of local exhaust ventilation, suitable respiratory protective equipment should be used.
- To fill and coat the surfaces: Use NEOPAL STUCCO.
- For new surfaces or porous surfaces coated with lime or low quality paints: Prime with NEOPAL PRIMER ECO for interior or VIVECRYL PRIMER for exterior surfaces.
- For the refinishing of sound surfaces apply directly **NEOPAL RELIEF**.

APPLICATION

- Ready for use. Stir well before use. If needed, is thinned up to 15% with clean water.
- After the preparation apply using a special roller in order to achieve the desirable textured pattern.
- You can recoat the surface with SUPER NEOPAL for interior or VIVECRYL PRIMER for exterior surfaces.
- Ensure good ventilation during application and drying.
- Apply the paint and let it dry at temperatures between 10°C to 35°C.

AFTER USE – WASTE MANAGEMENT

Remove as much paint as possible from brushes and rollers before cleaning • Clean brushes and equipment with water and detergent solution after use.

HEALTH, SAFETY & ENVIRONMENTAL INFORMATION

Keep out of reach of children • If medical advice is needed, have product container or label at hand • Do not get in eyes, on skin, or on clothing • Call a POISON CENTER or doctor if you feel unwell • Contains biocidal product: 1,2-benzisothiazol-3(2H)-one and reaction mass of 5-chloro-2-methyl-4-isothiazolin-3-one and 2-methyl-2H-isothiazol-3-one (3:1). May produce an allergic reaction • Do not empty into drains • Dispose of contents and container in accordance with all national regulations • Warning! Hazardous respirable droplets may be formed when sprayed. Do not breathe spray or mist.

Poison Center for Greece: +30210 7793777 / For Cyprus: 1401

Lift with care – gross weight exceeds 10 kg

**STIR WELL BEFORE USE - PROTECT FROM FROST
DO NOT APPLY AT TEMPERATURES UNDER 10°C.**



www.vivechrom.gr

Vivechrom Dr STEFANOS D. PATERAS SA
FACTORY & HEAD OFFICES: THESI VATHI PIGADI, 19600 MANDRA ATTICA, GREECE TEL.:+30 210 5538700, FAX:+30 210 5550464
THESSALONIKI: ETHN. ANTISTASEOS 114, 55134 KALAMARIA, TEL.:+30 2310 450000, FAX:+30 2310 493984